
Datum : 29.06.2016

Beschreibung: **Baufolie, transluzent**
Identifikationsnummer: 12081/100/1 Struktur: mono

Produktbeschreibung:

PE-Baufolie aus Polyethylene, transluzent

Rohstoff:

LDPE Sekundärrohstoff aus Produktionsabfällen, Haussammlungen, Industrieabfällen

Technische Daten:

Abmessung:	Breite: nach Anforderung Kunde Rollenlänge: nach Anforderung Kunde
Folienstärke:	variabel nach den Erfordernissen des Kunden in Anlehnung an DIN 53370
Schrumpfwert:	entfällt
Schmelzindex:	0,25 – 0,40 g/cm ³ (190°C/2, 16 kg) nach DIN 53735
Dichte:	0,92 – 0,93 g/m ³
Reissfestigkeit:	MD > 120 N/50 mm; CMD > 120 N/50 mm nach EN 12311-2
Reissdehnung:	MD > 400 %, CMD > 400% nach EN12311-2
Nadelung:	möglich
Wasserdampfdurchlässigkeit:	nicht geprüft
Wasserdampfdiffusionswiderstandszahl „my“	nicht geprüft
Wasserdampfdiffusionsäquivalente Luftschichtdicke „sd-Wert“	nicht geprüft

Die Angaben bezüglich der Materialbeschaffenheit (Dichte, Schmelzindex, Reissfestigkeit, Reissdehnung) sind Aussagen unserer Rohstofflieferanten. Keine Gewährleistung bei UV-Schäden (Folie immer abdecken!)

Dokument ohne Unterschrift

This technical data sheet serves excluding the improvement of the technical information according to the today's state of our knowledge, nevertheless, contains no assurance of properties. Besides the information provided in this refers only to the indicated item. The shown technical properties refer to new material with the generally tolerances. All technical characteristics can be changed without pre advice. The customer must judge the suitability of the product for the intended use and purpose himself; in this respect atravis carries neither responsibility nor guarantee. Our technical advice is only an expression of our opinion. Although this is given according to our best of knowledge, it is neither a basis for nor representation or statements of facts. This is valid even if proprietary rights of a third party are involved. Against commercial customers our product liability is strictly limited to the value invoiced when purchased. The liability for secondary damages is excluded, also the liability for light to middle carelessness.